

Date: Page: 1 of 2 Report No. C409901 Date: Jul. 07, 2004

TEST REPORT

APPLICANT

Chia Chang Co., Ltd.

No. 38, Ta Feng St, Lu Chu Hsiang,

Taoyuan Country, Taiwan, R.O.C.

SAMPLE DESCRIPTION

Two (2) pieces of submitted samples said to be:

Item name : Aluminum Coated Steel (Back Cover)

Date sample received: Jun. 30, 2004

Date test started: Jun. 30, 2004

TEST CONDUCTED

As requested by the applicant, for details please refer to attached page.

Prepared and checked by: For Intertek Testing Services Taiwan Limited



Jacob Lin General Manager

This report shall not be reproduced except in full, without the written approval of the laboratory.

Intertek Testing Services Taiwan Ltd.

14F, 27, Chung Shan North Road, Sec. 3, Taipei, Taiwan, R.O.C.

全國公證檢驗股份有限公司

台北市中山北路三段 27 號 14 樓

Tel: (+886-2) 2592-6033 · 2597-9955 Fax: (+886-2) 2593-6566



Date: Page: 2 of 2 Report No. C409901 Date: Jul. 07, 2004

TEST CONDUCTED

(A) Test result summary:

Testing item	Result (ppm)
	Submitted samples
Arsenic (As) content / 砷含量	ND
Beryllium (Be) content / 鈹含量	ND
Cadmium (Cd) content / 鎘含量	ND
Lead (Pb) content / 鉛含量	ND
Mercury (Hg) content / 汞含量	ND
Chromium VI (Cr ⁶⁺) content / 六價鉻含量	ND

Remarks: ppm = Parts per million

ND = Not detected

(B) Test method:

<u>Testing item</u>	<u>Testing method</u>	Reporting limit
Arsenic (As) content 砷含量	With reference to USEPA 3052, by microwave digestion and determined by ICP-OES	2 ppm
Beryllium (Be) content 鈹含量	With reference to USEPA 3052, by microwave digestion and determined by ICP-OES	2 ppm
Cadmium (Cd) content 鎘含量	With reference to USEPA 3052, by microwave digestion and determined by ICP-OES	2 ppm
Lead (Pb) content 鉛含量	With reference to USEPA 3052, by microwave digestion and determined by ICP-OES	2 ppm
Mercury (Hg) content 汞含量	With reference to USEPA 3052, by microwave digestion and determined by ICP-OES	2 ppm
Chromium VI (Cr ⁶⁺) content 六價鉻含量	With reference to USEPA 3060A & 7196A, by alkaline digestion and determined by UV-Vis	1 ppm

Remark :Reporting limit = Quantitation limit of analyte in sample solution

- END -